

■ HARVI III • UJDV • Unequal Flute Spacing • Roughing

Material Group	Side Milling (A)		short			medium			long			Recommended feed per tooth (fz = mm/th) for side milling (A).								
	A		adaptor reach									D1 – Diameter								
			KCSM15			KCSM15			KCSM15											
	ap		ae		Cutting Speed – vc m/min			Cutting Speed – vc m/min			Cutting Speed – vc m/min			mm	10,0	12,0	16,0	20,0	25,0	32,0
	min		max	min		max	min		max	min		max								
P	4	Ap max	0,4 x D	90	–	150	81	–	135	81	–	135	fz	0,046	0,053	0,065	0,075	0,083	0,087	
	5	Ap max	0,4 x D	60	–	100	51	–	85	48	–	80	fz	0,041	0,048	0,059	0,069	0,077	0,084	
M	1	Ap max	0,4 x D	90	–	115	72	–	92	63	–	80,5	fz	0,051	0,060	0,074	0,086	0,097	0,105	
	2	Ap max	0,4 x D	60	–	80	48	–	64	42	–	56	fz	0,041	0,048	0,059	0,069	0,077	0,084	
	3	Ap max	0,4 x D	60	–	70	48	–	56	42	–	49	fz	0,034	0,040	0,048	0,055	0,060	0,062	
S	1	Ap max	0,4 x D	50	–	90	40	–	72	30	–	54	fz	0,051	0,060	0,074	0,086	0,097	0,105	
	2	Ap max	0,4 x D	25	–	40	20	–	32	15	–	24	fz	0,027	0,032	0,039	0,046	0,052	0,057	
	3	Ap max	0,4 x D	25	–	40	20	–	32	15	–	24	fz	0,027	0,032	0,039	0,046	0,052	0,057	
	4	Ap max	0,4 x D	50	–	60	40	–	48	30	–	36	fz	0,038	0,044	0,055	0,063	0,071	0,077	
H	1	Ap max	0,4 x D	80	–	140	64	–	112	48	–	84	fz	0,046	0,053	0,065	0,075	0,083	0,087	
	2	Ap max	0,4 x D	70	–	120	56	–	96	42	–	72	fz	0,034	0,040	0,048	0,055	0,060	0,062	

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
 Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.
 Above parameters are based on ideal conditions. Please adjust parameters according to system stability.
 For side milling with ap larger than 1 x D, reduce fz by 20%!
 Cylindrical shanks not recommended for full slotting.

■ HARVI III • UJDV • Unequal Flute Spacing • Finishing

Material Group	Side Milling (A)		short			medium			long			Recommended feed per tooth (fz = mm/th) for side milling (A).								
	A		adaptor reach									D1 – Diameter								
			KCSM15			KCSM15			KCSM15											
	ap		ae		Cutting Speed – vc m/min			Cutting Speed – vc m/min			Cutting Speed – vc m/min			mm	10,0	12,0	16,0	20,0	25,0	32,0
	min		max	min		max	min		max	min		max								
P	4	Ap max	0,06 x D	171	–	285	153,9	–	256,5	153,9	–	256,5	fz	0,046	0,053	0,065	0,075	0,083	0,087	
	5	Ap max	0,06 x D	114	–	190	96,9	–	161,5	91,2	–	152	fz	0,041	0,048	0,059	0,069	0,077	0,084	
M	1	Ap max	0,06 x D	171	–	218,5	136,8	–	174,8	119,7	–	152,95	fz	0,051	0,060	0,074	0,086	0,097	0,105	
	2	Ap max	0,06 x D	114	–	152	91,2	–	121,6	79,8	–	106,4	fz	0,041	0,048	0,059	0,069	0,077	0,084	
	3	Ap max	0,06 x D	114	–	133	91,2	–	106,4	79,8	–	93,1	fz	0,034	0,040	0,048	0,055	0,060	0,062	
S	1	Ap max	0,06 x D	95	–	171	76	–	136,8	57	–	102,6	fz	0,051	0,060	0,074	0,086	0,097	0,105	
	2	Ap max	0,06 x D	47,5	–	76	38	–	60,8	28,5	–	45,6	fz	0,027	0,032	0,039	0,046	0,052	0,057	
	3	Ap max	0,06 x D	47,5	–	76	38	–	60,8	28,5	–	45,6	fz	0,027	0,032	0,039	0,046	0,052	0,057	
	4	Ap max	0,06 x D	95	–	114	76	–	91,2	57	–	68,4	fz	0,038	0,044	0,055	0,063	0,071	0,077	
H	1	Ap max	0,06 x D	152	–	266	121,6	–	212,8	91,2	–	159,6	fz	0,046	0,053	0,065	0,075	0,083	0,087	
	2	Ap max	0,06 x D	133	–	228	106,4	–	182,4	79,8	–	136,8	fz	0,034	0,040	0,048	0,055	0,060	0,062	

NOTE: Lower value of cutting speed is used for high stock removal applications or for higher hardness (machinability) within group.
 Higher value of cutting speed is used for finishing applications or for lower hardness (machinability) within group.
 Above parameters are based on ideal conditions. Please adjust parameters according to system stability.
 For side milling with ap larger than 1 x D, reduce fz by 20%!
 Cylindrical shanks not recommended for full slotting.